



DSA Structural Amendments under review are highlighted in GRAY

Template 14-04

2001 CBC - Chapter 14A  
EXTERIOR WALL COVERINGS

Section - 1403A - VENEER

Subsection(s) - 1403A.5.6

1403A.5 Adhered Veneer

• • • •

1 *1403A.5.6 Bond strength and tests. Veneer shall develop a bond*  
2 *to the supporting element of sufficient strength to provide a work-*  
3 *ing shear stress of 50 psi (345 kPa).*

4  
5 *Not less than two shear tests shall be performed for the adhered*  
6 *veneer between the units and the supporting element. At least one*  
7 *shear test shall be performed at each building for each 5,000*  
8 *square feet (465 m<sup>2</sup>) of floor area or fraction thereof.*

9  
10 *The bond strength as determined by the tests shall have a mini-*  
11 *um shear strength of 100 psi (690 kPa).*