



DSA Structural Amendments under review are highlighted in GRAY

Template 19-01

2001 CBC - Chapter 19A
CONCRETE

Section - 1902A - DEFINITIONS

Subsection(s) - AIR-DRY WEIGHT

1 *AIR-DRYWEIGHT is the unit weight of a lightweight concrete*
2 *specimen cured for seven days with neither loss nor gain of mois-*
3 *ture at 60°F to 80°F (15.6°C to 26.7°C) and dried * * * in*
4 *50 ± 7 percent relative humidity at 73.4°F ± 2°F (23.0°C ±*
5 *1.1°C) until there is no more than 0.3 lb./ft.³ (4.8 kg/m³) change in*
6 *the unit weight for a seven-day period.*