



DSA Structural Amendments under review are highlighted in GRAY

Template 19-15

2001 CBC - Chapter 19A
CONCRETE

Section - 1905A - CONCRETE QUALITY, MIXING AND PLACING

Subsection(s) - 1905A.6.1.1

- 1 **1905A.6 Evaluation and Acceptance of Concrete.**
2
3 **1905A.6.1 Frequency of testing.**
4
5 **1905A.6.1.1** Samples for strength tests of each class of concrete
6 placed each day shall be taken not less than once a day, or not less
7 than once for each 50 cubic yards (345m³) of concrete, or not less
8 than once for each 2,000 square feet (186 m²) of surface area for
9 slabs or walls. Additional samples for seven-day compressive
10 strength tests shall be taken for each class of concrete at the begin-
11 ning of the concrete work or whenever the mix or aggregate is
12 changed.