



DSA Structural Amendments under review are highlighted in GRAY

Template 19-20

2001 CBC - Chapter 19A
CONCRETE

Section - 1905A - CONCRETE QUALITY, MIXING AND PLACING

Subsection(s) - 1905A.12.4

1 *1905A.12.4 When mixing concrete during freezing or near-freez-*
2 *ing weather, the mix shall have a temperature of at least 50°F*
3 *(10.0°C), but not more than 90°F (32.2°C). The concrete shall be*
4 *maintained at a temperature of at least 50°F (10.0°C) for not less*
5 *than 72 hours after placing. When necessary, concrete materials*
6 *shall be heated before mixing. Special precautions shall be taken*
7 *for the protection of transit-mixed concrete to maintain a tempera-*
8 *ture of at least 50°F (10.0°C).*