



DSA Structural Amendments under review are highlighted in GRAY

**Template 25-11**

**2001 CBC - Chapter 25A**  
**GYPSUM BOARD AND PLASTER**

**Section - 2508A - EXTERIOR PLASTER**

**Subsection(s) - 2508A.8**

1 **2508A.8 Preparation of Masonry and Concrete.** Surfaces  
2 shall be clean, free from efflorescence, sufficiently damp and  
3 rough to ensure proper bond. If surface is insufficiently rough,  
4 approved bonding agents or a portland cement dash bond coat  
5 mixed in proportions of one and one half parts volume of sand to  
6 one part volume of portland cement or plastic cement shall be ap-  
7 plied. *Approved bonding agents shall conform with the provisions*  
8 *of United States Government Military Specifications*  
9 *MIL-B-19235.* Dash bond coat shall be left undisturbed and shall  
10 be moist cured not less than 24 hours. When dash bond is applied,  
11 first coat of base coat plaster may be omitted. See Table 25A-D for  
12 thickness.